

# **Wall Flashing** 3238


outside.

Size (ID)	Std Weight	2000	304SS
In.	Lbs	20ga	20ga
3	0.45		
4	0.62		
5	0.84		
6	1.12		
7	1.35		
8	1.63		
9	1.94		
10	2.26		
11	2.47		
12	2.97		
13	3.30	Std	Optional
14	4.41	010	op.ioiiai
15	5.10		
16	5.60		
17	6.10		
18	6.74		
19	7.25		
20	7.68		
21	8.13		
22	8.94		
23	9.20		
24	11.25		



#### **Notes:**

Ordering one Wall Flashing provides you with both an inside and an outside flashing, total four halves. Flashing can be ordered with Raw collar with or without lip.





# Wall Flashing 3238

	Temperature Rating of Product Components						
°F	QF Wall F	Flashing			Sealant	s	
1100°							
500°							
390°							
250°		Optional - 304SS	3M Scotch Seal Metal Sealant 2084		Optional - Rock River Silicone Sealant	Optional - Red Devil HVAC/R High Temperature Silicone Sealant	
194° 0° -40°	Galvanized Steel			<b>Optional</b> - 3M Polyurethane Adhesive Sealant 560			<b>Optional</b> - Epoxy - 3M DP 125 Gray Sealant
-60°							

A	ddit	iona	I No	tes

At temperatures ranging between 390° F and 480° F, the zinc-iron alloy layers in galvanized steel will continue to provide a high level of protection from corrosion. However, there may be some peeling, changes in mechanical properties, and reduction in the corrosion protection. Recommended max. service temperature is 390° F.

## Optional - Seams can be solid welded

Rock River Silicone Sealant and Red Devil HVAC/R High Temperature Silicone Sealant are not paintable

### 304SS:

bluing may occur at 800° F and above

Compliance / Rating of Product Components		
Product	Material	Compliance / Rating
QF Wall Flashing	Galvanized	ASTM A653 with a G-90 rating
	304SS	Finish meets ASTM A240
	316SS	Finish meets ASTM A240
3M Scotch Seal Metal Sealant 2084	Acetone blend	AAMA Specification 801.1
3M Polyurethane Sealant 560	Polyurethane	ASTM E 162, ASTM E 662, Bombardier SP 800-C
Rock River Sealant	100% Silicone	ASTM C920 Class 25, TT-S-00230C Class A and TT-S-001543A, FDA No 421 CFR 117.2600, conforms to FDA requirements
Red Devil HVAC/R High Temperature Sealant	Silicone	ASTM C920 Class 25, TT-S-00230C Class A and TT-S-001543A, CEBTP 432.6 140-2, Mil Spec 46106A, CGSB 19C9-9B, DIN 18540 Part 2, OREX 150031-2

